



12/23/2020

2021-MDOT 21AA

Procedure	Sieve/Test	Average	Unit	MDOT 21AA Limestone
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	98.2	%	85-100
	3/4" (19mm)	86.7	%	
	1/2" (12.5mm)	67.5	%	50-75
	3/8" (9.5mm)	56.6	%	
	#4 (4.75mm)	36.8	%	
	#8 (2.36mm)	24.2	%	20-45
	#16 (1.18mm)	16.9	%	
	#30 (.6mm)	12.9	%	
	#50 (.3mm)	10.8	%	
	#100 (.15mm)	9.8	%	
	#200 (75µm)	8.92	%	
	-#200 (75um)	8.92	%	
	Wash Loss (#200/75um)	8.6	%	4.0-10.0
	Total Moisture	5.23	%	