



04/12/2021

100th Street  
 ASI #41-117  
 900 100th Street  
 Byron Center, MI 49315

**2021-MDOT 21AA**

Procedure	Sieve/Test	Average	Unit	MDOT 21AA Limestone
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	91.7	%	85-100
	3/4" (19mm)	75.4	%	
	1/2" (12.5mm)	53.2	%	50-75
	3/8" (9.5mm)	42.2	%	
	#4 (4.75mm)	28.1	%	
	#8 (2.36mm)	20.7	%	20-45
	#16 (1.18mm)	14.8	%	
	#30 (.6mm)	11.0	%	
	#50 (.3mm)	9.3	%	
	#100 (.15mm)	7.8	%	
	#200 (75µm)	6.91	%	
	-#200 (75um)	6.91	%	
	Grad Loss	0.000	%	
	Wash Loss (#200/75um)	6.5	%	4.0-10.0
	Total Moisture	4.64	%	

**Name/Title**

Dan Ferris / QC