



12/23/2020

2223-MI 23A Gravel

Procedure	Sieve/Test	Average	Unit	MDOT 23A Limestone
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	96.3	%	
	1/2" (12.5mm)	79.6	%	
	3/8" (9.5mm)	68.7	%	60-85
	#4 (4.75mm)	46.5	%	
	#8 (2.36mm)	32.7	%	25-60
	#16 (1.18mm)	24.5	%	
	#30 (.6mm)	19.7	%	
	#50 (.3mm)	16.9	%	
	#100 (.15mm)	15.4	%	
	#200 (75µm)	14.32	%	
	Fractured Faces (>1)	100.0	%	≥25.0
	-#200 (75um)	14.32	%	
	Wash Loss (#200/75um)	14.0	%	9.0-16.0
	Total Moisture	5.93	%	