



04/12/2021

100th Street
 ASI #41-117
 900 100th Street
 Byron Center, MI 49315

2223-MI 23A Gravel

Procedure	Sieve/Test	Average	Unit	MDOT 23A Limestone
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	96.8	%	
	1/2" (12.5mm)	82.1	%	
	3/8" (9.5mm)	71.0	%	60-85
	#4 (4.75mm)	48.6	%	
	#8 (2.36mm)	34.1	%	25-60
	#16 (1.18mm)	25.4	%	
	#30 (.6mm)	20.2	%	
	#50 (.3mm)	16.9	%	
	#100 (.15mm)	15.1	%	
	#200 (75µm)	13.96	%	
	-#200 (75um)	13.96	%	
	Wash Loss (#200/75um)	13.7	%	9.0-16.0
	Total Moisture	5.45	%	

Name/Title

Dan Ferris / QC