



04/12/2021

100th Street
 ASI #41-117
 900 100th Street
 Byron Center, MI 49315

2271-MI Class II Sand

Procedure	Sieve/Test	Average	Unit	MI Class II Sand Spec
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	100.0	%	
	#4 (4.75mm)	96.1	%	50-100
	#8 (2.36mm)	87.5	%	
	#16 (1.18mm)	78.4	%	
	#30 (.6mm)	65.6	%	
	#50 (.3mm)	33.9	%	
	#100 (.15mm)	4.1	%	0-30
	#200 (75µm)	1.30	%	
	-#200 (75um)	1.30	%	
	Wash Loss (#200/75um)	1.0	%	0.0-7.0
	Total Moisture	4.16	%	

Name/Title

Dan Ferris / QC