



04/12/2021

100th Street  
 ASI #41-117  
 900 100th Street  
 Byron Center, MI 49315

**2272-2NS Sand**

Procedure	Sieve/Test	Average	Unit	MDOT 2NS
	3/8" (9.5mm)	100.0	%	
	#4 (4.75mm)	95.6	%	95-100
	#8 (2.36mm)	80.7	%	65-95
	#16 (1.18mm)	67.3	%	35-75
	#30 (.6mm)	51.7	%	20-55
	#50 (.3mm)	22.0	%	10-30
	#100 (.15mm)	3.6	%	0-10
	#200 (75µm)	1.45	%	
	FM	2.79		
	Wash Loss (#200/75um)	1.2	%	
	Total Moisture	4.52	%	
	Cu	4.50		

**Name/Title**

Dan Ferris / QC