



04/12/2021

100th Street
ASI #41-117
900 100th Street
Byron Center, MI 49315

2370-Mfg Sand

Procedure	Sieve/Test	Average	Unit	2021 Target
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	77.5	%	73-89
	#8 (2.36mm)	43.2	%	40-56
	#16 (1.18mm)	26.4	%	24-36
	#30 (.6mm)	15.6	%	13-25
	#50 (.3mm)	9.2	%	5-17
	#100 (.15mm)	5.7	%	0-10
	#200 (75µm)	3.82	%	0-10
	Fractured Faces (>1)	98.9	%	
	-#200 (75um)	3.82	%	
	Wash Loss (#200/75um)	3.3	%	
	Total Moisture	4.22	%	

Name/Title

Dan Ferris / QC