

04/30/2021

2502-1"x3" Crushed Concrete

Procedure	Sieve/Test	Average	Unit	Ann Arbor 1 x 3's Recycled Concrete
	3 1/2" (90mm)	100.0	%	100-100
	3" (75mm)	100.0	%	
	2 1/2" (63mm)	82.2	%	
	2" (50mm)	40.4	%	
	1 1/2" (37.5mm)	11.9	%	
	1" (25mm)	1.6	%	
	3/4" (19mm)	0.9	%	
	1/2" (12.5mm)	0.9	%	
	3/8" (9.5mm)	0.7	%	

Name/Title

Josh Orshoski / QC Tech