

04/30/2021

2524-MDOT 21AA Recycled Crushed Concrete

Procedure	Sieve/Test	Average	Unit	MDOT 21AA Recycled Concrete
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	92.0	%	85-100
	3/4" (19mm)	83.1	%	
	1/2" (12.5mm)	66.7	%	50-75
	3/8" (9.5mm)	57.5	%	
	#4 (4.75mm)	42.0	%	
	#8 (2.36mm)	31.5	%	20-45
	#16 (1.18mm)	26.0	%	
	#30 (.6mm)	20.5	%	
	#50 (.3mm)	15.2	%	
	#100 (.15mm)	10.3	%	
	#200 (75µm)	5.89	%	4-10
	Wash Loss (#200/75µm)	5.2	%	4.0-10.0

Name/Title

Josh Orshoski / QC Tech