



04/30/2021

Burmeister
ASI # 81-93
6068 Steinbach Rd.
Ann Arbor, MI 48103

2063-MDOT 6A C Gravel

Procedure	Sieve/Test	Average	Unit	MDOT 6A
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	96.9	%	95-100
	3/4" (19mm)	64.6	%	
	1/2" (12.5mm)	36.4	%	30-60
	3/8" (9.5mm)	6.1	%	
	#4 (4.75mm)	2.5	%	0-8
	#8 (2.36mm)	2.2	%	
	Wash Loss (#200/75um)	0.8	%	0.0-1.0

Name/Title

Josh Orshoski / QC Tech