



04/30/2021

Burmeister
 ASI # 81-93
 6068 Steinbach Rd.
 Ann Arbor, MI 48103

2210-Peastone Gravel

| Procedure | Sieve/Test | Average | Unit | Peastone Gravel |
|-----------|-----------------------|---------|------|-----------------|
| | 3/4" (19mm) | 100.0 | % | 100-100 |
| | 1/2" (12.5mm) | 100.0 | % | |
| | 3/8" (9.5mm) | 88.4 | % | |
| | #4 (4.75mm) | 7.5 | % | |
| | #8 (2.36mm) | 2.3 | % | 0-5 |
| | #16 (1.18mm) | 1.7 | % | |
| | #30 (.6mm) | 1.4 | % | |
| | #50 (.3mm) | 1.2 | % | |
| | #100 (.15mm) | 1.0 | % | |
| | #200 (75µm) | 0.84 | % | |
| | Wash Loss (#200/75um) | 0.8 | % | 0.0-2.0 |

Name/Title

Josh Orshoski / QC Tech