



04/30/2021

Burmeister
ASI # 81-93
6068 Steinbach Rd.
Ann Arbor, MI 48103

2214-1x2 Gravel

| Procedure | Sieve/Test | Average | Unit |
|-----------|-----------------------|---------|------|
| | 3" (75mm) | 100.0 | % |
| | 2 1/2" (63mm) | 100.0 | % |
| | 2" (50mm) | 90.1 | % |
| | 1 1/2" (37.5mm) | 67.7 | % |
| | 1" (25mm) | 19.3 | % |
| | 3/4" (19mm) | 3.1 | % |
| | 1/2" (12.5mm) | 1.9 | % |
| | 3/8" (9.5mm) | 1.6 | % |
| | #4 (4.75mm) | 1.4 | % |
| | Wash Loss (#200/75um) | 0.7 | % |

Name/Title

Josh Orshoski / QC Tech