



04/30/2021

Burmeister  
ASI # 81-93  
6068 Steinbach Rd.  
Ann Arbor, MI 48103

### 2272-2NS Sand

Procedure	Sieve/Test	Average	Unit	ODOT Sand
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	97.7	%	95-100
	#8 (2.36mm)	89.5	%	70-100
	#16 (1.18mm)	71.0	%	38-80
	#30 (.6mm)	53.7	%	18-60
	#50 (.3mm)	23.1	%	5-30
	#100 (.15mm)	4.9	%	0-10
	#200 (75µm)	1.60	%	0-5
	Wash Loss (#200/75um)	1.4	%	

Name/Title

Josh Orshoski / QC Tech