



04/30/2021

Burmeister  
 ASI # 81-93  
 6068 Steinbach Rd.  
 Ann Arbor, MI 48103

**2488-Wayne Co. Porous Grade B**

Procedure	Sieve/Test	Average	Unit	Wayne Co. Porous Grade B
	2" (50mm)	100.0	%	100-100
	1" (25mm)	100.0	%	
	3/4" (19mm)	93.9	%	
	1/2" (12.5mm)	63.6	%	45-85
	3/8" (9.5mm)	49.5	%	
	#4 (4.75mm)	45.1	%	20-85
	#8 (2.36mm)	38.5	%	
	#16 (1.18mm)	31.2	%	
	#30 (.6mm)	23.2	%	5-30
	#50 (.3mm)	11.6	%	
	#100 (.15mm)	3.9	%	
	#200 (75µm)	2.26	%	0-5
	Wash Loss (#200/75um)	2.1	%	0.0-5.0

**Name/Title**

Josh Orshoski / QC Tech