



04/30/2021

Denniston  
ASI # 58-009  
15203 S. Telegraph  
Monroe, MI 48161

### 2002-MI 1" X 3" LIMESTONE

Procedure	Sieve/Test	Average	Unit	MI 1x3's
	3" (75mm)	100.0	%	
	2 1/2" (63mm)	87.6	%	
	2" (50mm)	71.4	%	
	1 1/2" (37.5mm)	31.8	%	
	1" (25mm)	10.6	%	
	3/4" (19mm)	4.5	%	
	1/2" (12.5mm)	2.8	%	
	3/8" (9.5mm)	2.1	%	
	#4 (4.75mm)	1.6	%	
	#8 (2.36mm)	1.2	%	
	Wash Loss (#200/75um)	0.5	%	0.0-3.0

Name/Title

Josh Orshoski / QC Tech