



04/30/2021

Denniston  
 ASI # 58-009  
 15203 S. Telegraph  
 Monroe, MI 48161

**2004-4 Limestone**

Procedure	Sieve/Test	Average	Unit	Ballast 4's
	2 1/2" (63mm)	100	%	
	2" (50mm)	100	%	100-100
	1 1/2" (37.5mm)	92	%	90-100
	1" (25mm)	22	%	20-55
	3/4" (19mm)	12	%	0-15
	1/2" (12.5mm)	7	%	
	3/8" (9.5mm)	4	%	0-5
	#4 (4.75mm)	2	%	
	#8 (2.36mm)	2	%	
<hr/>				
	Wash Loss (#200/75um)	1.3	%	0.0-2.0

**Name/Title**

Josh Orshoski / QC Tech