



04/30/2021

Denniston  
ASI # 58-009  
15203 S. Telegraph  
Monroe, MI 48161

### 2006-MDOT 6AA /ODOT57 Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 6AA
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	99.6	%	95-100
	3/4" (19mm)	82.4	%	
	1/2" (12.5mm)	46.8	%	30-60
	3/8" (9.5mm)	29.1	%	
	#4 (4.75mm)	6.3	%	0-8
	#8 (2.36mm)	2.5	%	
	Wash Loss (#200/75um)	1.4	%	0.0-2.0

Name/Title

Josh Orshoski / QC Tech