



04/30/2021

Denniston  
ASI # 58-009  
15203 S. Telegraph  
Monroe, MI 48161

### 2010-MI Screenings Limestone

| Procedure | Sieve/Test            | Average | Unit | MI Screenings |
|-----------|-----------------------|---------|------|---------------|
|           | 1/2" (12.5mm)         | 100.0   | %    | 100-100       |
|           | 3/8" (9.5mm)          | 99.9    | %    | 95-100        |
|           | #4 (4.75mm)           | 84.1    | %    | 80-100        |
|           | #8 (2.36mm)           | 52.8    | %    |               |
|           | #16 (1.18mm)          | 34.5    | %    |               |
|           | #30 (.6mm)            | 24.7    | %    |               |
|           | #50 (.3mm)            | 19.2    | %    |               |
|           | #100 (.15mm)          | 16.7    | %    | 10-30         |
|           | #200 (75µm)           | 15.74   | %    |               |
|           | Wash Loss (#200/75um) | 14.9    | %    |               |

Name/Title

Josh Orshoski / QC Tech