



04/30/2021

Denniston
ASI # 58-009
15203 S. Telegraph
Monroe, MI 48161

2021-MI 21AA Comm Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 21A Com.
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	97.0	%	
	3/4" (19mm)	89.5	%	
	1/2" (12.5mm)	76.3	%	
	3/8" (9.5mm)	67.8	%	
	#4 (4.75mm)	50.4	%	
	#8 (2.36mm)	36.1	%	
	#16 (1.18mm)	25.8	%	
	#30 (.6mm)	19.5	%	
	#50 (.3mm)	15.6	%	
	#100 (.15mm)	13.6	%	
	#200 (75µm)	12.40	%	
	Wash Loss (#200/75um)	11.7	%	

Name/Title

Josh Orshoski / QC Tech