



04/30/2021

Denniston  
ASI # 58-009  
15203 S. Telegraph  
Monroe, MI 48161

### 2071-MFG. SAND Limestone

Procedure	Sieve/Test	Average	Unit	2071 MFG Sand
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	92.9	%	
	#8 (2.36mm)	56.8	%	
	#16 (1.18mm)	27.4	%	
	#30 (.6mm)	12.3	%	
	#50 (.3mm)	5.5	%	
	#100 (.15mm)	4.1	%	
	#200 (75µm)	3.98	%	
	Wash Loss (#200/75um)	3.7	%	

Name/Title

Josh Orshoski / QC Tech