

2072-Class II Limestone Sand

Procedure	Sieve/Test	Average	Unit	Class II Limestone Sand
	3" (75mm)	100.0	%	≤100
	2 1/2" (63mm)	100.0	%	
	2" (50mm)	100.0	%	
	1 1/2" (37.5mm)	100.0	%	
	1" (25mm)	100.0	%	60-100
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	100.0	%	
	#4 (4.75mm)	93.4	%	50-100
	#8 (2.36mm)	60.2	%	
	#10 (2mm)	50.6	%	
	#16 (1.18mm)	30.2	%	
	#30 (.6mm)	15.1	%	
	#40 (.425mm)	9.8	%	
	#50 (.3mm)	6.8	%	
	#100 (.15mm)	5.0	%	0-30
	#200 (75µm)	5.02	%	
	Wash Loss (#200/75µm)	4.3	%	0.0-7.0
ASTM C70	Total Moisture	6.5	%	