



04/05/2021

Denniston
 ASI # 58-009
 15203 S. Telegraph
 Monroe, MI 48161

2073.3-MDOT Class IIIA

Procedure	Sieve/Test	Average	Unit	MDOT Class IIIA
	6" (150mm)	100.0	%	100-100
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	93.8	%	50-100
	#8 (2.36mm)	62.0	%	
	#16 (1.18mm)	33.2	%	
	#30 (.6mm)	17.3	%	
	#50 (.3mm)	9.4	%	
	#100 (.15mm)	7.0	%	0-30
	#200 (75µm)	6.5	%	
AASHTO T11	-#200 (75um)	6.52	%	
	Grad Loss	0.000	%	
	Wash Loss (#200/75um)	6.3	%	0.0-15.0

Name/Title

Scott George / QC Tech