



04/30/2021

Denniston
 ASI # 58-009
 15203 S. Telegraph
 Monroe, MI 48161

2109-Washed 9's Limestone

Procedure	Sieve/Test	Average	Unit	Denniston 9's
	3/8" (9.5mm)	100.0	%	100-100
	1/4" (6.3mm)	85.8	%	
	#4 (4.75mm)	39.2	%	
	#8 (2.36mm)	3.1	%	
	#16 (1.18mm)	1.6	%	
	#30 (.6mm)	1.2	%	
	#50 (.3mm)	1.1	%	
	#100 (.15mm)	0.9	%	
	#200 (75µm)	0.9	%	
	Wash Loss (#200/75um)	0.8	%	

Name/Title

Josh Orshoski / QC Tech