



Denniston
Pit # 58-009
15203 S. Telegraph
Monroe, MI 48161
(734) 241-8966

08/16/2017

2121-MDOT 21AA Spec. Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 21AA Spec.
	1 1/2" (37.5mm)	100	%	100-100
	1" (25mm)	96	%	85-100
	3/4" (19mm)	85	%	
	1/2" (12.5mm)	68	%	50-75
	3/8" (9.5mm)	58	%	
	#4 (4.75mm)	43	%	
	#8 (2.36mm)	27	%	20-45
	#16 (1.18mm)	16	%	
	#30 (0.6mm)	11	%	
	#50 (0.3mm)	9	%	
	#100 (0.15mm)	8	%	
	#200 (75µm)	7	%	4-10
	Pan	0	%	
	Wash Loss (#200/75um)	6.9	%	4-10