



06/08/2017

### 2002-1"x3" Limestone

Procedure	Sieve/Test	Average	Unit	1"x 3" Limestone
	3 1/2" (90mm)	100.0	%	100-100
	3" (75mm)	100.0	%	
	2 1/2" (63mm)	92.8	%	
	2" (50mm)	61.8	%	
	1 1/2" (37.5mm)	40.3	%	
	1" (25mm)	10.7	%	
	3/4" (19mm)	3.9	%	
	1/2" (12.5mm)	3.8	%	
	Pan	0.00	%	
	Wash Loss (#200/75um)	2.0	%	