



04/30/2021

Grand Rapids Rail Yard
Flint, Lansing, Grand Rapids, MI

2023-MDOT 23A

Procedure	Sieve/Test	Average	Unit	MDOT 23A
	1 1/2" (37.5mm)	100.0	%	
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	95.8	%	
	1/2" (12.5mm)	78.7	%	
	3/8" (9.5mm)	67.6	%	60-85
	#4 (4.75mm)	46.0	%	
	#8 (2.36mm)	32.3	%	25-60
	#16 (1.18mm)	23.8	%	
	#30 (.6mm)	19.1	%	
	#50 (.3mm)	15.8	%	
	#100 (.15mm)	13.8	%	
	#200 (75µm)	12.59	%	9-16
	Grad Loss	0.006	%	
	Wash Loss (#200/75um)	12.2	%	9.0-16.0

Name/Title

Josh Orshoski / QC Tech