



01/14/2021

2521-21AA Crushed Concrete

Procedure	Sieve/Test	Average	Unit	MDOT 21 AA
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	93.2	%	85-100
	3/4" (19mm)	84.7	%	
	1/2" (12.5mm)	72.5	%	50-75
	3/8" (9.5mm)	62.2	%	
	#4 (4.75mm)	49.9	%	
	#8 (2.36mm)	39.6	%	20-45
	#16 (1.18mm)	35.4	%	
	#30 (.6mm)	28.6	%	
	#50 (.3mm)	20.0	%	
	#100 (.15mm)	12.8	%	
	#200 (75µm)	9.18	%	
	Wash Loss (#200/75um)	7.6	%	4.0-10.0
	Total Moisture	11.9	%	