



04/30/2021

Grand Rapids Rail Yard  
 Flint, Lansing, Grand Rapids, MI

**2521-21AA Crushed Concrete**

<b>Procedure</b>	<b>Sieve/Test</b>	<b>Average</b>	<b>Unit</b>	<b>MDOT 21 AA</b>
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	92.7	%	85-100
	3/4" (19mm)	82.9	%	
	1/2" (12.5mm)	70.2	%	50-75
	3/8" (9.5mm)	59.9	%	
	#4 (4.75mm)	46.9	%	
	#8 (2.36mm)	37.0	%	20-45
	#16 (1.18mm)	32.9	%	
	#30 (.6mm)	26.8	%	
	#50 (.3mm)	18.9	%	
	#100 (.15mm)	11.9	%	
	#200 (75µm)	8.40	%	
	Wash Loss (#200/75um)	7.0	%	4.0-10.0

**Name/Title**

Josh Orshoski / QC Tech