



04/12/2021

Grand Rapids Rail Yard
 Flint, Lansing, Grand Rapids, MI

2002-1"x3" Limestone

Procedure	Sieve/Test	Average	Unit	1"x 3" Limestone
	3 1/2" (90mm)	100.0	%	100-100
	3" (75mm)	100.0	%	
	2 1/2" (63mm)	91.7	%	
	2" (50mm)	75.0	%	
	1 1/2" (37.5mm)	54.7	%	
	1" (25mm)	23.1	%	
	3/4" (19mm)	9.7	%	
	1/2" (12.5mm)	5.7	%	
	Wash Loss (#200/75um)	0.7	%	
	Total Moisture	1.7	%	

Name/Title

Dan Ferris / QC