



04/12/2021

Grand Rapids Rail Yard  
 Flint, Lansing, Grand Rapids, MI

**2004-OH 4**

Procedure	Sieve/Test	Average	Unit	OH #4
	2" (50mm)	100.0	%	100-100
	1.12" (28mm)	100.0	%	
	1" (25mm)	54.8	%	20-55
	3/4" (19mm)	13.7	%	0-15
	1/2" (12.5mm)	5.7	%	
	3/8" (9.5mm)	4.2	%	0-5
	#4 (4.75mm)	3.4	%	
	#8 (2.36mm)	3.1	%	
	#16 (1.18mm)	3.0	%	
	#30 (.6mm)	2.8	%	
	#50 (.3mm)	2.7	%	
	#100 (.15mm)	2.4	%	
	#200 (75µm)	1.88	%	
<hr/>				
	Wash Loss (#200/75um)	1.7	%	
	Total Moisture	2.0	%	

Name/Title

Dan Ferris / QC