



04/12/2021

Grand Rapids Rail Yard
 Flint, Lansing, Grand Rapids, MI

2023-MDOT 23A

Procedure	Sieve/Test	Average	Unit	MDOT 23A
	1 1/2" (37.5mm)	100.0	%	
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	96.3	%	
	1/2" (12.5mm)	79.5	%	
	3/8" (9.5mm)	70.0	%	60-85
	#4 (4.75mm)	50.7	%	
	#8 (2.36mm)	37.9	%	25-60
	#16 (1.18mm)	28.8	%	
	#30 (.6mm)	22.4	%	
	#50 (.3mm)	18.0	%	
	#100 (.15mm)	14.4	%	
	#200 (75µm)	10.82	%	9-16
	FM	4.61		
	Wash Loss (#200/75um)	10.1	%	9.0-16.0
	Total Moisture	4.1	%	

Name/Title

Dan Ferris / QC