



12/23/2020

2121-MDOT 21AA Spec.

Procedure	Sieve/Test	Average	Unit
	1 1/2" (37.5mm)	100.0	%
	1" (25mm)	94.2	%
	3/4" (19mm)	84.3	%
	1/2" (12.5mm)	74.0	%
	3/8" (9.5mm)	65.4	%
	#4 (4.75mm)	43.4	%
	#8 (2.36mm)	28.7	%
	#16 (1.18mm)	20.1	%
	#30 (.6mm)	14.9	%
	#50 (.3mm)	12.0	%
	#100 (.15mm)	10.5	%
	#200 (75µm)	9.53	%
	FM	5.21	
	Wash Loss (#200/75um)	9.4	%
	Total Moisture	8.5	%