



04/12/2021

Grand Rapids Rail Yard  
Flint, Lansing, Grand Rapids, MI

### 2121-MDOT 21AA Spec.

Procedure	Sieve/Test	Average	Unit
	1 1/2" (37.5mm)	100.0	%
	1" (25mm)	90.5	%
	3/4" (19mm)	76.4	%
	1/2" (12.5mm)	58.3	%
	3/8" (9.5mm)	50.1	%
	#4 (4.75mm)	35.7	%
	#8 (2.36mm)	26.1	%
	#16 (1.18mm)	20.9	%
	#30 (.6mm)	17.3	%
	#50 (.3mm)	15.0	%
	#100 (.15mm)	12.0	%
	#200 (75µm)	9.88	%
	FM	5.46	
	Wash Loss (#200/75um)	9.4	%
	Total Moisture	4.6	%

Name/Title

Dan Ferris / QC