



04/30/2021

Grand Rapids Rail Yard
 Flint, Lansing, Grand Rapids, MI

2002-1"x3" Limestone

Procedure	Sieve/Test	Average	Unit	1"x 3" Limestone
	3 1/2" (90mm)	100.0	%	100-100
	3" (75mm)	100.0	%	
	2 1/2" (63mm)	86.5	%	
	2" (50mm)	75.6	%	
	1 1/2" (37.5mm)	51.2	%	
	1" (25mm)	16.6	%	
	3/4" (19mm)	8.8	%	
	1/2" (12.5mm)	7.4	%	
	Wash Loss (#200/75um)	1.6	%	

Name/Title

Josh Orshoski / QC Tech