



04/30/2021

Grand Rapids Rail Yard  
Flint, Lansing, Grand Rapids, MI

### 2006.5-MDOT 6AA Wyandot Dolomite

Procedure	Sieve/Test	Average	Unit	MDOT 6AA
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	100.0	%	95-100
	3/4" (19mm)	90.6	%	
	1/2" (12.5mm)	49.3	%	30-60
	3/8" (9.5mm)	24.4	%	
	#4 (4.75mm)	8.6	%	0-8
	#8 (2.36mm)	5.1	%	
	Wash Loss (#200/75um)	2.0	%	0.0-2.0

Name/Title

Josh Orshoski / QC Tech