



04/30/2021

Maybe
ASI # 58-004
6837 Scofield Road
Maybe, MI 48159

2021-MI 21AA COMM

Procedure	Sieve/Test	Average	Unit	MI 21AA COMM
	1 1/2" (37.5mm)	100	%	100-100
	1" (25mm)	100	%	
	3/4" (19mm)	93	%	
	1/2" (12.5mm)	72	%	
	3/8" (9.5mm)	60	%	
	#4 (4.75mm)	43	%	
	#8 (2.36mm)	33	%	
	#16 (1.18mm)	27	%	
	#30 (.6mm)	23	%	
	#50 (.3mm)	20	%	
	#100 (.15mm)	16	%	
	#200 (75µm)	14	%	
	Wash Loss (#200/75um)	12.6	%	

Name/Title

Josh Orshoski / QC Tech