



04/30/2021

Maybe  
 ASI # 58-004  
 6837 Scofield Road  
 Maybe, MI 48159

**2023-MDOT 23A**

Procedure	Sieve/Test	Average	Unit	MDOT 23A
	1" (25mm)	100	%	100-100
	3/4" (19mm)	99	%	
	1/2" (12.5mm)	86	%	
	3/8" (9.5mm)	72	%	60-85
	#4 (4.75mm)	44	%	
	#8 (2.36mm)	29	%	25-60
	#16 (1.18mm)	21	%	
	#30 (.6mm)	17	%	
	#50 (.3mm)	14	%	
	#100 (.15mm)	12	%	
	#200 (75µm)	10	%	9-16
<hr/>				
	Wash Loss (#200/75um)	9.3	%	9.0-16.0

**Name/Title**

Josh Orshoski / QC Tech