



04/30/2021

Maybe
ASI # 58-004
6837 Scofield Road
Maybe, MI 48159

2107-MI. 6AA Comm.

Procedure	Sieve/Test	Average	Unit
	1 1/2" (37.5mm)	100.0	%
	1" (25mm)	100.0	%
	3/4" (19mm)	85.9	%
	1/2" (12.5mm)	41.4	%
	3/8" (9.5mm)	22.7	%
	#4 (4.75mm)	4.2	%
	#8 (2.36mm)	2.3	%
	Wash Loss (#200/75um)	1.3	%

Name/Title

Josh Orshoski / QC Tech