



04/30/2021

Maybe
ASI # 58-004
6837 Scofield Road
Maybe, MI 48159

2110-MDOT FA II

Procedure	Sieve/Test	Average	Unit	MDOT FA II
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	95.3	%	90-100
	#8 (2.36mm)	67.7	%	65-90
	#16 (1.18mm)	46.4	%	45-70
	#30 (.6mm)	32.8	%	30-50
	#50 (.3mm)	23.4	%	18-30
	#100 (.15mm)	14.7	%	10-21
	#200 (75µm)	11.02	%	5-15
	Wash Loss (#200/75um)	10.5	%	

Name/Title

Josh Orshoski / QC Tech