



04/12/2021

Moscow  
 ASI # 30-71  
 8760 East Chicago Rd  
 Horton, MI 49246

**2206-6A**

Procedure	Sieve/Test	Average	Unit	MDOT 6A
	1" (25mm)	99.7	%	95-100
	3/4" (19mm)	83.6	%	
	1/2" (12.5mm)	36.8	%	30-60
	3/8" (9.5mm)	14.6	%	
	#4 (4.75mm)	1.5	%	0-8
	#8 (2.36mm)	1.3	%	
	#16 (1.18mm)	1.3	%	
	#30 (.6mm)	1.2	%	
	#50 (.3mm)	1.1	%	
	#100 (.15mm)	1.1	%	
	#200 (75µm)	0.85	%	
ASTM C-131	LA Abrasion (B,500)	21.9	%	
	Wash Loss (#200/75um)	0.8	%	0.0-2.0
ASTMC127	Absorption	1.4	%	
	Total Moisture	2.22	%	
ASTMC127	SPGR (Dry,Gsb)	2.632		
ASTMC127	SPGR (SSD)	2.669		
ASTMC127	SPGR (Apparent,Gsa)	2.732		
ASTM C29	Unit Wt (Loose)	93	lb/ft3	
ASTM C29	Unit Wt (Rodded)	103	lb/ft3	
ASTM C29	Unit Wt SSD (Loose)	94	lb/ft3	
ASTM C29	Unit Wt SSD (Rodded)	104	lb/ft3	
ASTM C29	Voids (Loose)	43	%	
ASTM C29	Voids (Rodded)	37	%	

Name/Title

Dan Ferris / QC