



04/12/2021

Moscow
 ASI # 30-71
 8760 East Chicago Rd
 Horton, MI 49246

2218-Birdseye

Procedure	Sieve/Test	Average	Unit	2021 Target
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	77.5	%	69-89
	#8 (2.36mm)	15.0	%	6-26
	#16 (1.18mm)	4.2	%	0-15
	#30 (.6mm)	2.0	%	
	#50 (.3mm)	1.6	%	
	#100 (.15mm)	1.4	%	
	#200 (75µm)	1.16	%	
ASTM C-131	LA Abrasion (D,500)	21.5	%	
	FM	4.982		
	Wash Loss (#200/75um)	1.0	%	
ASTMC127	Absorption	2.0	%	
	Total Moisture	2.77	%	
ASTMC127	SPGR (Dry,Gsb)	2.578		
ASTMC127	SPGR (SSD)	2.631		
ASTMC127	SPGR (Apparent,Gsa)	2.721		
ASTM C29	Unit Wt (Loose)	100	lb/ft3	
ASTM C29	Unit Wt (Rodded)	107	lb/ft3	
ASTM C29	Unit Wt SSD (Loose)	102	lb/ft3	
ASTM C29	Unit Wt SSD (Rodded)	109	lb/ft3	
ASTM C29	Voids (Loose)	38	%	
ASTM C29	Voids (Rodded)	34	%	

Name/Title

Dan Ferris / QC