



04/12/2021

Moscow
 ASI # 30-71
 8760 East Chicago Rd
 Horton, MI 49246

2222-MI 22A GRAVEL

Procedure	Sieve/Test	Average	Unit	2222-MI 22A GRAVEL
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	95.2	%	90-100
	1/2" (12.5mm)	83.7	%	
	3/8" (9.5mm)	77.1	%	65-85
	#4 (4.75mm)	61.7	%	
	#8 (2.36mm)	48.0	%	30-50
	#16 (1.18mm)	37.2	%	
	#30 (.6mm)	27.6	%	
	#50 (.3mm)	17.5	%	
	#100 (.15mm)	11.2	%	
	#200 (75µm)	7.99	%	
<hr/>				
	FM	4.245		
	Fractured Faces (>1)	54	%	≥25
	Wash Loss (#200/75um)	7.6	%	4.0-8.0
	Total Moisture	6.96	%	

Name/Title

Dan Ferris / QC