



04/12/2021

Moscow
 ASI # 30-71
 8760 East Chicago Rd
 Horton, MI 49246

2223-MI 23A Gravel

Procedure	Sieve/Test	Average	Unit	MI 23A Gravel Spec
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	94.3	%	
	1/2" (12.5mm)	82.7	%	
	3/8" (9.5mm)	76.7	%	60-85
	#4 (4.75mm)	62.7	%	
	#8 (2.36mm)	51.8	%	25-60
	#16 (1.18mm)	43.1	%	
	#30 (.6mm)	34.2	%	
	#50 (.3mm)	23.8	%	
	#100 (.15mm)	16.3	%	
	#200 (75µm)	12.71	%	
	Fractured Faces (>1)	55	%	25-100
	Wash Loss (#200/75um)	12.1	%	8.5-16.0
	Total Moisture	6.69	%	

Name/Title

Dan Ferris / QC