



Moscow
 Pit # 30-71
 8760 East Chicago Rd
 Horton, MI 49246

11/10/2018

2227-MDOT Class II Sand

Procedure	Sieve/Test	Average	Unit	Class II Sand
	3" (75mm)	100.0	%	100-100
	2" (50mm)	100.0	%	
	1" (25mm)	100.0	%	60-100
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	100.0	%	
	#4 (4.75mm)	90.1	%	50-100
	#8 (2.36mm)	57.5	%	
	#16 (1.18mm)	38.0	%	
	#30 (0.6mm)	26.9	%	
	#50 (0.3mm)	18.4	%	
	#100 (0.15mm)	11.0	%	0-30
	#200 (75µm)	7.00	%	0-7
<hr/>				
	FM	3.580		
	Wash Loss (#200/75um)	6.6	%	0-7
	Total Moisture	6.02	%	
	Cu	19.70		