



04/12/2021

Moscow
 ASI # 30-71
 8760 East Chicago Rd
 Horton, MI 49246

2268-2NS Premium

Procedure	Sieve/Test	Average	Unit	2NS Prem
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	92.4	%	65-95
	#16 (1.18mm)	69.4	%	35-75
	#30 (.6mm)	40.8	%	20-55
	#50 (.3mm)	12.4	%	10-30
	#100 (.15mm)	2.4	%	0-10
	#200 (75µm)	1.27	%	0-3
	FM	2.826		
	Wash Loss (#200/75um)	1.2	%	0.0-3.0
ASTM C128	Absorption	1.3	%	
	Total Moisture	5.01	%	
	Cu	3.70		
ASTM C128	SPGR (Dry,Gsb)	2.598		
ASTM C128	SPGR (SSD)	2.633		
ASTM C128	SPGR (Apparent,Gsa)	2.690		
ASTM C29	Unit Wt (Loose)	104	lb/ft3	
ASTM C29	Unit Wt (Rodded)	110	lb/ft3	
ASTM C29	Unit Wt SSD (Loose)	105	lb/ft3	
ASTM C29	Unit Wt SSD (Rodded)	111	lb/ft3	
ASTM C29	Voids (Loose)	36	%	
ASTM C29	Voids (Rodded)	32	%	

Name/Title

Dan Ferris / QC