



04/30/2021

Newport  
 ASI # 58-011  
 7250 Reaume Road  
 Newport, MI 48166

**2002-MI 1" X 3" LIMESTONE**

<b>Procedure</b>	<b>Sieve/Test</b>	<b>Average</b>	<b>Unit</b>	<b>1 x 3's Production</b>
	3" (75mm)	100.0	%	80-100
	2 1/2" (63mm)	82.0	%	
	2" (50mm)	62.8	%	
	1 1/2" (37.5mm)	31.9	%	
	1" (25mm)	4.8	%	
	3/4" (19mm)	2.7	%	
	Wash Loss (#200/75um)	1.0	%	0.0-2.0

**Name/Title**

Josh Orshoski / QC Tech