



04/30/2021

Newport
ASI # 58-011
7250 Reaume Road
Newport, MI 48166

All Sampling and testing are performed with accordance ASTM Section 4 Construction Volume 4.02 and MDOT

2006-6A MI Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 6AA
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	98.8	%	95-100
	3/4" (19mm)	79.2	%	
	1/2" (12.5mm)	43.7	%	30-60
	3/8" (9.5mm)	27.2	%	
	#4 (4.75mm)	6.1	%	0-8
	#8 (2.36mm)	3.0	%	
	Grad Loss	0.000	%	
	Wash Loss (#200/75um)	1.4	%	0.0-2.0

All Sampling and testing are performed with accordance ASTM Section 4 Construction Volume 4.02 and MDOT

Name/Title

Josh Orshoski / QC Tech