



04/30/2021

Newport
ASI # 58-011
7250 Reaume Road
Newport, MI 48166

2017-17A MI Limestone

Procedure	Sieve/Test	Average	Unit	17A MI Limestone
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	97.9	%	90-100
	1/2" (12.5mm)	64.5	%	50-75
	3/8" (9.5mm)	40.0	%	
	#4 (4.75mm)	7.1	%	0-8
	#8 (2.36mm)	2.7	%	
	Wash Loss (#200/75um)	1.1	%	0.0-2.0

Name/Title

Josh Orshoski / QC Tech