



04/30/2021

Newport
ASI # 58-011
7250 Reaume Road
Newport, MI 48166

2021-MI 21AA Commercial

Procedure	Sieve/Test	Average	Unit	MI 21AA Commercial
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	93.7	%	85-100
	3/4" (19mm)	79.8	%	
	1/2" (12.5mm)	63.4	%	50-75
	3/8" (9.5mm)	55.2	%	
	#4 (4.75mm)	38.9	%	
	#8 (2.36mm)	27.7	%	20-45
	#16 (1.18mm)	20.4	%	
	#30 (.6mm)	16.2	%	
	#50 (.3mm)	13.2	%	
	#100 (.15mm)	11.4	%	
	#200 (75µm)	10.31	%	
	Wash Loss (#200/75um)	9.9	%	

Name/Title

Josh Orshoski / QC Tech