



04/30/2021

Newport
 ASI # 58-011
 7250 Reaume Road
 Newport, MI 48166

2022-MDOT 22A Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 22A Limestone
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	98.0	%	90-100
	1/2" (12.5mm)	91.4	%	
	3/8" (9.5mm)	76.2	%	65-85
	#4 (4.75mm)	48.8	%	
	#8 (2.36mm)	32.1	%	30-50
	#16 (1.18mm)	21.6	%	
	#30 (.6mm)	15.5	%	
	#50 (.3mm)	11.5	%	
	#100 (.15mm)	9.7	%	
	#200 (75µm)	8.87	%	4-10
Wash Loss (#200/75um)		8.6	%	4.0-10.0

Name/Title

Josh Orshoski / QC Tech